

英制钢球压碎载荷值
STEEL BALL CRUSH LOAD VALUE (BY INCH)

钢球公称直径 Diameter		压碎载荷 Crushing Load N		钢球公称直径 Diameter		压碎载荷 Crushing Load N	
inch	mm	热处理后 After Heat-treatment	成品 Finished Product	inch	mm	热处理后 After Heat-treatment	成品 Finished Product
1/8	3.1750	4210	5390	11/16	17.4625	127010	154840
5/32	3.6988	6570	8430	23/32	18.2562	138770	168560
3/16	4.7628	9410	12050	3/4	19.0500	151120	183260
7/32	5.5562	12840	16270	25/32	19.8438	164050	198940
15/64	5.9531	14800	18130	13/16	20.6375	177380	214620
1/4	6.3500	16760	21270	7/8	22.2250	203700	246960
17/64	6.7463	18910	24000	29/32	23.0188	220700	257740
9/32	7.1438	21270	26950	15/16	23.8125	236180	281260
5/16	7.9375	26260	32830	1	24.4000	368720	318500
11/32	8.7312	31750	39690	1 1/16	26.9875	303310	357700
3/8	9.5250	37830	47040	1 1/8	28.5750	340060	396900
13/32	10.3188	44390	54880	1 3/16	30.1625	378970	441000
7/16	11.1125	51450	63700	1 1/4	31.7500	419830	487060
29/64	11.5094	55470	68600	1 5/16	33.3375	462950	534100
15/32	11.9062	59000	73500	1 3/8	34.9250	508030	582129
31/64	12.3031	63010	78400	1 7/8	36.5125	555270	632100
1/2	12.7000	67130	83300	1 1/2	38.1000	604560	689000
17/32	13.4938	75850	94080	1 5/8	41.2750	709520	798700
9/16	14.2875	85060	104860	1 11/16	42.8625	765180	852600
19/32	15.0812	94770	116620	1 3/4	44.4500	822910	911400
5/8	15.8750	104960	128380	1 7/8	47.6250	944720	1038800
21/32	16.6688	115740	142100	2	50.8000	1074860	1166200